## **CENTELLEN® R 3825**



# CENTELLEN<sup>®</sup> R 3825 – gasket sheet with best gas tightness and great stress relaxation for temperatures up to 200°C.

Centellen<sup>®</sup> R 3825 consists of aramid fibers, inorganic fibers as well as mineral fillers for reinforcement bonded with NBR.

Centellen<sup>®</sup> R 3825 is a material with best gas tightness and great stress relaxation at a temperature range up to 200°C.

This gasket sheet was developed with applications in mind like waste water, heating industry as well as the engineering industry.

The material is suitable for hydrocarbons like oils or solvents, alcohols, glycols, aqueous solutions, water and steam.

**Basis composition** Aramid fibers bonded with NBR.

 Color
 Yellow / Yellow

 Certificates
 in progress (BAM tested)



Manufactured by KLINGER

| Sheet size                        | 1000 x 1500 mm, 2000 x 1500 mm  |
|-----------------------------------|---|
| Thickness                         | 0.5 mm, 1.0 mm, 1.5 mm,<br>2.0 mm, 3.0 mm<br>Other thicknesses on request |
| Tolerances                        |   |
| Thickness acc<br>Length:<br>Width | ording to DIN 28091-1<br>± 50 mm<br>± 50 mm                               |

#### Industry

General Industry / Chemical / Oil & Gas / Energy / Infrastructure / Pulp & Paper

TECHNICAL DATA - Typical values for a thickness of 2.0 mm

| Density                        |                             | g/cm <sup>3</sup> | 1.75  |
|--------------------------------|-----------------------------|-------------------|-------|
| Compressibility                | ASTM F 36 J                 | %                 | 9     |
| Recovery                       | ASTM F 36 J                 | %                 | 55    |
| Stress relaxation DIN 52913    | 50 MPa, 16 h/175°C          | MPa               | 25    |
| KLINGER cold/hot compression   | thickness decrease at 23°C  | %                 | 13    |
| 50 MPa                         | thickness decrease at 300°C | %                 | 28    |
| Tightness                      | DIN 28090-2                 | mg/(s x m)        | 0.01  |
| Thickness increase after fluid | oil IRM 903: 5 h/150°C      | %                 | 8     |
| immersion ASTM F 146           | fuel B: 5 h/23°C            | %                 | 10    |
| Cold compression               | DIN 28090-2                 | %                 | 8     |
| Cold recovery                  | DIN 28090-2                 | %                 | 5     |
| Hot compression                | DIN 28090-2                 | %                 | 27    |
| Hot recovery                   | DIN 28090-2                 | %                 | 4     |
| Max. surface pressure EN 13555 | 23°C                        | N/mm <sup>2</sup> | > 200 |
|                                | 175°C                       | N/mm <sup>2</sup> | > 200 |

#### **CENTELLEN® R 3825**



### Chemical resistance chart

Simplified overview of the chemical resistance depending on the most important groups of raw materials:

| CENTELLEN® R 3825         |               |          |                                      |              | A: small or no attack |         | B: weak till moderate attack |       |       | C: strong attack  |                   |
|---------------------------|---------------|----------|--------------------------------------|--------------|-----------------------|---------|------------------------------|-------|-------|-------------------|-------------------|
| Paraffinic<br>hydrocarbon | Motor<br>fuel | Aromates | Chlorinated<br>hydrocarbon<br>fluids | Motor<br>oil | Mineral<br>lubricants | Alcohol | Ketone                       | Ester | Water | Acid<br>(diluted) | Base<br>(diluted) |
| Α                         | В             | С        | С                                    | Α            | В                     | Α       | С                            | С     | Α     | Α                 | Α                 |

All information is based on years of experience in production and operation of sealing elements. However, in view of the wide variety of possible installation and operating conditions one cannot draw final conclusions in all application cases regarding the behaviour in gasket joint. The data may not, therefore, be used to support any warranty claims. This edition cancels all previous issues. Subject to change without notice.



Certified acc. to DIN EN ISO 9001:2015 Subject to technical alterations. Status: November 2022 Rich. Klinger Dichtungstechnik GmbH & Co KG / Am Kanal 8-10 / A-2352 Gumpoldskirchen, Austria Tel +43 (0) 2252/62599-137 / Fax +43 (0) 2252/62599-296 / e-mail: marketing@klinger.co.at

#### www.centellen.eu

picture on the left. A statement about the expected tightness of the flange connection is only possible if a qualified and defined installation

of the gasket has been executed.